



Kabebari batten detail

Profile: Round Single 22x18mm


Base: 0.084kg/m Cover: 0.15kg/m Total: 0.234kg/m *End cover: 0.167kg/m Batten thickness: 1.0mm End cap thickness: 2.5mm





22

*End cover



12

14.4

22

4.8

3. 5


1.2

8.3

22


18. 1

11




1.2

2.5








			Product Name Ever Art Wood - Kabebari				Project Name	Creation Date	Page	Scale	Projection
$\underline{\lambda}$		Never strike extrusion directly with a hammer or rubber mallet. Use a pine plank between the tool and the extrusion to avoid surface damage or denting.				bari	Round Single 22x18		1 of 3	1:1	⊕
Λ	End caps	Secure to batten with screw or exterior grade adhesive (Sikaflex), OR Screw fix or apply exterior grade adhesive (Sikaflex) to secure cap to batten.	Approval	Chek	Drawing	Design	Customer	Distributor		Manufacturer	
No.	DATE	Secon into apply extend grade dancaste (Sikanek) to secone cap to batteri.	1					CO	coveť		Kasho

Endcap detail

17.5

 Λ




				Product Name Ever Art Wood - Kabebari				Project Name	Creation Date	Page	Scale	Projection
$\frac{1}{2}$	L Inst		Never strike extrusion directly with a hammer or rubber mallet. Use a pine plank between the tool and the extrusion to avoid surface damage or denting.				bari	Round Double 44.5x18		2 of 3	1:1	♦母
$\overline{1}$	End		Secure to batten with screw or exterior grade adhesive (Sikaflex), OR Screw fix or apply exterior grade adhesive (Sikaflex) to secure cap to batten.	Approval Chek Drawing Design			Design	Customer	Distributor		Manufacturer	
N	. D	DATE							coveť		Takasho	

Drawing Number

Kabebari batten detail

Profile: Round Double 44.5x18mm

Installation detail 🛕



Kabebari Batten Installation Guide

- Aluminium can be damaged if mishandled. Never strike directly with a hammer or rubber mallet. Use a pine plank between the striking rubber mallet and the extrusion to avoid surface damage or denting.
- Cut aluminium with a drop saw using an aluminium blade.
- Always cap ends of extrusions with supplied end caps or a flashing to avoid moisture ingress.
- Plastic end caps must be securely inserted with screws supplied or sikafelx applied to the inside of the extrusion before inserting. This will prevent slippage of the extrusion.
- Metal end caps (painted) must be screwed to the extrusion.
- All end caps can only be applied to straight 90 degree cuts. They cannot be applied to angle end cuts.
- Ensure appropriate screws are used to suit the substrate you are fastening to. It is important to use stainless steel or bi-metal screws for all metal surfaces impacted when fastening (i.e. furring channels, top hats, steel frames). This will prevent galvanic reaction between the screw/substrate and aluminium extrusion.
- Fasten at maximum 1 metre spans. Please contact Covet for further information.
- Always fasten the male (base) section first. The female (top section) clips over the top. They can also slide on if necessary.

A			Product Name Ever Art Wood - Kabebari				Project Name	Creation Date	Page	Scale	Projection
Δ		Never strike extrusion directly with a hammer or rubber mallet. Use a pine plank between the tool and the extrusion to avoid surface damage or denting.				bari	Round Double 44.5x18		3 of 3	1:1	♦₽
Λ	End caps	Secure to batten with screw or exterior grade adhesive (Sikaflex), OR Screw fix or apply exterior grade adhesive (Sikaflex) to secure cap to batten.	Approval	Chek	Drawing	Design	Customer	Distributor		Manufacturer	
No.	DATE							CO	veť	" Takasho	